

## **Product Specification – LEgeo RG2010**

Product Type:	Woven Fiberglass Geogrid
Geogrid Coating:	Modified Polymer

Index Properties	Test method	Units	MD value <sup>1</sup>	XMD value <sup>1</sup>
Ultimate tensile strength	ASTM D6637-01	kN/m (lbs/in)	100 (570)	200 (1,140)
<ul> <li>Tensile Elongation at failure</li> </ul>	ASTM D6637-01	%	< 3.0	
• Aperture Size <sup>2</sup>	Nominal	mm (in)	12.5 (0.5)	12.5 (0.5)
Melting Point	ASTM D276	°C (°F)	> 300 (570)	
Mass per Unit Area	ASTM D5261	g/m <sup>2</sup> (oz/yd <sup>2</sup> )	580	(17.1)
Roll Physical Properties	Units	Value		
• Roll Width (standard) <sup>3</sup>	m (ft)	1.5 (5.0)		
<ul> <li>Roll Length (standard)<sup>3</sup></li> </ul>	m (ft)	75 (246)		
• Roll Weight (standard) <sup>3</sup>	kg (lbs)	85 (188)		

## Notes:

- 1. Unless indicated otherwise, values shown are Minimum Average Roll Values (MARV) in accordance with ASTM D4759-02.
- 2. Measured centerline to centerline.
- 3. Standard Roll Sizes, custom roll size available upon request.

**DISCLAIMER:** L.E. Geosolutions reserves the right to change its product specifications at any time and without notice. It is the user's responsibility to ensure that this specification is current and that the specified product is appropriate for the application being considered.